

CLIENT: **CRANE COMPOSITES**
Attn: Michelle Bauer
8015 Dixon Drive
Florence, KY 41042

Test Report No: TJ1557-1	Date: October 3, 2013
---------------------------------	------------------------------

SAMPLE ID: The Client submitted and identified the following test material as “**STC .090**”

SAMPLING DETAIL: Test samples were submitted to the laboratory directly by the client. No special sampling conditions or sample preparation were observed by QAI.

DATE OF RECEIPT: Samples were received at QAI facilities on September 5, 2013

TESTING PERIOD: September 25, 2013


AUTHORIZATION: Proposal FB-2013-082701 approved on September 29, 2013

TEST REQUESTED: Perform standard flame spread and smoke density developed classification tests on the sample supplied by the Client in accordance with ASTM Designation E84-12, "Standard Method of Test for Surface Burning Characteristics of Building Materials". The foregoing test procedure is comparable to UL 723, ANSI/NFPA No. 255, and UBC No. 8-1.

TEST RESULTS:	<u>Flame Spread</u>	<u>Smoke Developed</u>
	130	200

CLASSIFICATION: The material tested resulted in a Class C. Detailed test results are presented in the subsequent pages of this report

Prepared By


Jared Weise
Fire Test Technician

**Signed for and on behalf of
QAI Laboratories, Inc.**


J. Brian McDonald
Operations Manager



PREPARATION AND CONDITIONING: The sample was submitted in six 4 foot long panels measuring 21 inches wide and approximately 0.09 inches thick. The sample material was placed into conditioning at 73°F (±5°F) and 50% (±5%) relative humidity until day of testing.

E 84 TEST DATA SHEET:

MOUNTING METHOD: The sample was self-supporting and placed along the ledges of the tunnel during testing. No additional mounting method was used

CLIENT: Crane Composites **DATE:** September 25, 2013

SAMPLE: STC .090

IGNITION: 0 minutes, 40 seconds

FLAME FRONT: 19 feet maximum

TIME TO MAXIMUM SPREAD: 3 minutes, 00 seconds

TEST DURATION: 10 minutes, 00 seconds

SUMMARY: **FLAME SPREAD:** 130 (131.8 unrounded) **SMOKE DEVELOPED:** 200 (219 unrounded)

OBSERVATIONS:

Fairly rapid flame spread noted from start. After about 3 minutes the flames maxed out at window 19. A slow flame recession was then noted. Moderate smoke generation was displayed and some after flame was noted upon test completion.

CALIBRATION DATA:

Time to Ignition of Last Red Oak (sec):	57
Red Oak Smoke Area (%A*Min):	111
Total Fuel Burned (ft³)	59.68



SUMMARY OF ASTM E84 RESULTS:




Because of the possible variations in reproducibility, the results are adjusted to the nearest figure divisible by 5. Smoke Density values over 200 are rounded to the nearest figure divisible by 50.

In order to obtain the Flame Spread Classification, the above results should be compared to the following table:

<u>NFPA CLASS</u>	<u>IBC CLASS</u>	<u>FLAME SPREAD</u>	<u>SMOKE DEVELOPED</u>
A	A	0 through 25	Less than or equal to 450
B	B	26 through 75	Less than or equal to 450
C	C	76 through 200	Less than or equal to 450

BUILDING CODES CITED:

1. National Fire Protection Association, ANSI/NFPA No. 101, "Life Safety Code", 2006 Edition.
2. International Building Code, 2006 Edition, Chapter 8, Interior Finishes, Section 803.



END OF REPORT

THIS REPORT IS THE CONFIDENTIAL PROPERTY OF THE CLIENT ADDRESSED. THE REPORT MAY ONLY BE REPRODUCED IN FULL. PUBLICATION OF EXTRACTS FROM THIS REPORT IS NOT PERMITTED WITHOUT WRITTEN APPROVAL FROM QAI. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED FOR THE INDIVIDUAL PROJECT FILE REFERENCED. THE RESULTS OF THIS REPORT PERTAIN ONLY TO THE SPECIFIC SAMPLE(S) EVALUATED.