

CLIENT: Crane Composites
8015 Dixon Dr.
Florence KY 41042

Test Report No: TJ2392-1	Date: September 12, 2014
---------------------------------	---------------------------------

SAMPLE ID: The client identified the following test material as “**STDSC.120**”

SAMPLING DETAIL: Test samples were submitted to the laboratory directly by the client. No special sampling conditions or sample preparation were observed by QAI.

DATE OF RECEIPT: Samples were received at QAI facilities on September 3, 2014

TESTING PERIOD: September 5, 2014

AUTHORIZATION: Signed work order FB-2014-020702.

TEST REQUESTED: Perform standard flame spread and smoke density developed classification tests on the sample supplied by the Client in accordance with ASTM Designation E84-13, "Standard Method of Test for Surface Burning Characteristics of Building Materials". The foregoing test procedure is comparable to UL 723, ANSI/NFPA No. 255, and UBC No. 8-1.

TEST RESULTS:	<u>Flame Spread</u>	<u>Smoke Developed</u>
	60	450

CLASSIFICATION: The material resulted in a class “B”. Detailed test results are presented in the subsequent pages of this report

Prepared By



Jeff Foster
Fire Test Technician

**Signed for and on behalf of
QAI Laboratories, Inc.**



J. Brian McDonald
Operations Manager

PREPARATION AND CONDITIONING: The sample was submitted in six panels approximately 4 feet long measuring 24 inches wide and approximately .119 inches thick. The sample material was placed into conditioning at 73°F ($\pm 5^\circ\text{F}$) and 50% ($\pm 5\%$) relative humidity until day of testing.

E 84 TEST DATA SHEET:

MOUNTING METHOD: The sample was supported during testing by 2" hexagonal mesh poultry netting running the length of the test chamber and 1/4" round metal rods placed at 2' intervals across the width of the test chamber, with cement board place between the sample and tunnel lid.

CLIENT: Crane Composites **DATE:** September 12, 2014

SAMPLE: STDSC.120

IGNITION: 1 minute, 30 seconds

FLAME FRONT: 19 feet maximum

TIME TO MAXIMUM SPREAD: 5 minutes, 30 seconds

TEST DURATION: 10 minutes, 00 seconds

SUMMARY: FLAME SPREAD: 60 (62.1 unrounded) **SMOKE DEVELOPED:** 450 (475 unrounded)

OBSERVATIONS:

Sustained ignition began at 1 minute 30 seconds, with charring shortly after at 1 minute 35 seconds. Slow flame propagation until 3 minutes 30 seconds, when flame moved down the tunnel to 19 feet, with very heavy smoke. There was after burn witnessed at the conclusion of the 10 minute test.

CALIBRATION DATA:

Time to Ignition of Last Red Oak (sec):	54
Red Oak Smoke Area (%A * Min):	109.7
Total Fuel Burned (ft ³)	50.21

SUMMARY OF ASTM E84 RESULTS:



Because of the possible variations in reproducibility, the results are adjusted to the nearest figure divisible by 5. Smoke Density values over 200 are rounded to the nearest figure divisible by 50.

In order to obtain the Flame Spread Classification, the above results should be compared to the following table:

<u>NFPA CLASS</u>	<u>IBC CLASS</u>	<u>FLAME SPREAD</u>	<u>SMOKE DEVELOPED</u>
A	A	0 through 25	Less than or equal to 450
B	B	26 through 75	Less than or equal to 450
C	C	76 through 200	Less than or equal to 450


BUILDING CODES CITED:

1. National Fire Protection Association, ANSI/NFPA No. 101, "Life Safety Code", 2006 Edition.
2. International Building Code, 2006 Edition, Chapter 8, Interior Finishes, Section 803.



THIS REPORT IS THE CONFIDENTIAL PROPERTY OF THE CLIENT ADDRESSED. THE REPORT MAY ONLY BE REPRODUCED IN FULL. PUBLICATION OF EXTRACTS FROM THIS REPORT IS NOT PERMITTED WITHOUT WRITTEN APPROVAL FROM QAI. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED FOR THE INDIVIDUAL PROJECT FILE REFERENCED. THE RESULTS OF THIS REPORT PERTAIN ONLY TO THE SPECIFIC SAMPLE(S) EVALUATED.

Temperature - Time Curve



END OF TEST REPORT